

Styrolux 684D

Styrene Butadiene Copolymer (SBC)

TECHNICAL
DATASHEET

DESCRIPTION

Styrolux® 684D is a clear styrene-butadiene copolymer (SBC) used in injection molding for parts with enhanced toughness as well as in sheet and film extrusion and blow molding. Parts made of Styrolux® 684D reveal excellent printability.

FEATURES

- High clarity
- Improved toughness
- Good printability

APPLICATIONS

- Food and non-food packaging
- Container, cups and lids
- Toys
- Extruded sheet and thin film
- Medical devices
- Blow moldings

| Property, Test Condition | Standard | Unit | Values |
|---------------------------------------|-------------|------------|--------|
| Rheological Properties | | | |
| Melt Volume Rate, 200 °C/5 kg | ISO 1133 | cm³/10 min | 11 |
| Mechanical Properties | | | |
| Izod Notched Impact Strength, 23 °C | ISO 180/A | kJ/m² | 4 |
| Izod Notched Impact Strength, -30 °C | ISO 180/A | kJ/m² | 3 |
| Charpy Notched Impact Strength, 23° C | ISO 179/1eA | kJ/m² | 4 |
| Tensile Stress at Yield, 23 °C | ISO 527 | MPa | 26 |
| Tensile Strain at Yield, 23 °C | ISO 527 | % | 2.3 |
| Nominal Strain at Break, 23 °C | ISO 527 | % | 160 |
| Tensile Modulus | ISO 527 | MPa | 1500 |
| Tensile Creep Modulus (1000h) | ISO 899 | MPa | 790 |
| Tensile Creep Modulus (1h) | ISO 899 | MPa | 1300 |
| Flexural Strength, 23 °C | ISO 178 | MPa | 40 |
| Flexural Modulus, 23 °C | ISO 178 | MPa | 1700 |
| Hardness, Shore D | ISO 868 | - | 68 |
| Thermal Properties | | | |
| | | | |

Styrolux 684D

Styrene Butadiene Copolymer (SBC)

TECHNICAL
DATASHEET

| Property, Test Condition | Standard | Unit | Values |
|---|-------------|----------------------|---------|
| Vicat Softening Temperature VST/B/50 (50N, 50 °C/h) | ISO 306 | °C | 59 |
| Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h) | ISO 306 | °C | 83 |
| Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa) | ISO 75 | °C | 65 |
| Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa) | ISO 75 | °C | 75 |
| Coefficient of Linear Thermal Expansion | ISO 11359 | 10 ⁻⁶ /°C | 60 - 90 |
| Electrical Properties | | | |
| Optical Properties | | | |
| Refractive Index, Sodium D Line | ISO 489 | - | 1.575 |
| Light Transmission at 550 nm | ASTM D 1003 | % | 89 |
| Haze | ASTM D 1003 | % | < 2 |
| Other Properties | | | |
| Density | ISO 1183 | kg/m ³ | 1010 |
| Water Absorption, Saturated at 23 °C | ISO 62 | % | 0.07 |
| Processing | | | |
| Linear Mold Shrinkage | ISO 294-4 | % | 0.3 - 1 |

Typical values for uncolored products

SUPPLY FORM

Styrolux is supplied in pellet form and should be kept in its original containers in cool, dry place. Avoid direct exposure to sunlight. Styrolux® can be stored in silos at temperatures well below 45 °C.

PRODUCT SAFETY

During processing of Styrolux® small quantities of styrene monomer may be released into the atmosphere. At styrene vapor concentrations below 20 ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well ventilated workplaces - that is where five to eight air changes per hour are made. For safety information please refer to our Material Safety Data Sheet for this product.

Styrolux 684D

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.
