INEOS STYROLUTION

Terlux 2812

Methyl Methacrylate Acrylonitrile Butadiene Styrene (MABS)

TECHNICAL DATASHEET

DESCRIPTION

Terlux® 2812 is an easy-flowing injection molding grade based on a MABS polymer. Terlux® 2812 offers an unique combination of properties, such as a balanced stiffness/toughness ratio and the high transparency well known in SAN molding compositions.

FEATURES

- Excellent transparency
- Good resistance to chemicals
- Good Stiffness and surface finish
- High impact strength
- Easy-flow grade

APPLICATIONS

- Cosmetic packaging
- Homeware
- Housings
- Toys, sport and leisure

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm³/10 min	8
Melt Volume Rate, 220 °C/21.6 kg	ISO 1133	cm³/10 min	45
Mechanical Properties			
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m²	5
Charpy Notched Impact Strength, -30 °C	ISO 179/1eA	kJ/m²	2
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m²	110
Charpy Unnotched, -30 °C	ISO 179/1eU	kJ/m²	70
Tensile Stress at Yield, 23 °C	ISO 527	MPa	42
Tensile Strain at Yield, 23 °C	ISO 527	%	4
Tensile Modulus	ISO 527	MPa	1900
Nominal Strain at Break, 23 °C	ISO 527	%	20
Flexural Strength, 23 °C	ISO 178	MPa	60
Hardness, Ball Indentation	ISO 2039-1	MPa	75
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	87
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	87

Contact us:
Phone +49 (2133) 9309 – 168
INSTY.emea@ineos.com
www.ineos-styrolution.com

Revision Date: 2016.01.17

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	93
Coefficient of Linear Thermal Expansion	ISO 11359	10^{-6}/°C	80 - 110
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 62631-2-1	-	3
Dissipation Factor (100 Hz)	IEC 62631-2-1	10^{-4}	160
Dissipation Factor (1 MHz)	IEC 62631-2-1	10^{-4}	130
Volume Resistivity	IEC 62631-3-1	Ohm*m	10^{14}
Surface Resistivity	IEC 62631-3-1	Ohm	10^{15}
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.54
Other Properties			
Density	ISO 1183	kg/m³	1080
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	230 - 260
Mold Temperature Range	ISO 294	°C	50 - 75
Injection Velocity	ISO 294	mm/s	200
Drying Temperature	-	°C	70
Drying Time	-	h	2

Typical values for uncolored products

PROCESSING

Terlux is primarily processed through injection molding but any process suitble for thermoplastic molding compositions may also be used.

Contact us:
Phone +49 (2133) 9309 – 168
INSTY.emea@ineos.com
www.ineos-styrolution.com

DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.

Contact us:
Phone +49 (2133) 9309 – 168
INSTY.emea@ineos.com
www.ineos-styrolution.com